








**BRISBANE  
MOSS**

M Chapman & Sons Textiles Ltd  
Chapman Works  
Manchester Road  
Dunnockshaw  
Burnley  
Lancashire  
United Kingdom  
BB11 5PW

Tel: 01706 815121  
sales@chapmangroup.co.uk  
www.chapmangroup.co.uk

Tel: 01706 815121  
sales@brisbanemoss.co.uk  
www.brisbanemoss.co.uk

Technical Document		Article-	GS20		Release Date-	01 November 2024
Description-	8 Wale Heavyweight Corduroy			Composition-	100% Cotton	
Applications-	Apparel					
Weight (g/m2)	565			UNI 5114		
Weight Linear (g/m)	848					
Warp Yarn per Inch	46			UNI EN 1049/2		
Weft Yarn per Inch	280					
Warp Yarn Count	3/24s			ISO 7211/5		
Weft Yarn Count	16s					
Minimum Usable Width	146cm			UNI EN 1773		
Customs Tariff Code (HS)	58012200					
County of Origin	Italy					
Yarn Origin	USA/Turkey					
Weaving Origin	Italy					
Dyeing/Finishing Origin	Italy					
Sample/Bulk Leadtime (Weeks)	Stock Supported					
Manufacturing Features-						
Piece Dye	Jig Dyeing Method		Reactive Dyestuffs			
Care Instructions-						UNI EN ISO 3758
<div></div>						
Dimensional Stability-						
Domestic Washing	Warp	+/- 3%		ISO 6330:2021		
	Weft	+/- 3%				
Steam Ironing	Warp	+/- 3%		DIN 53894-2		
	Weft	+/- 3%				
Dry Cleaning	Warp	+/- 3%		UNI EN ISO 3175-2		
	Weft	+/- 3%				
Physical Features-						
Tensile Strength	Warp	180kg		UNI EN ISO 13934-1		
	Weft	110kg				
Tear Strength	Warp	2800g		UNI EN ISO 13927-2		
	Weft	2100g				
Seam Slippage (6mm)	Warp	> 20kg		UNI EN ISO 13935-1		
	Weft	> 20kg				
Abrasion Resistance (9kPa)	Face	Grade 4/5 @ 30,000 Rubs		UNI EN ISO 12947-2		
Pilling (2000 Revolutions)	Face	Grade 4/5		UNI EN ISO 12945-2		
Martindale	Face	Grade 4/5		20,000rpm		
Maximum Weft Skew			3%			
Stretch and Recovery at 30N Load	Extension	N/A		UNI EN 14704-1		
	Residual	N/A				

**BRISBANE  
MOSS**





**BRISBANE  
MOSS**

M Chapman & Sons Textiles Ltd  
Chapman Works  
Manchester Road  
Dunnockshaw  
Burnley  
Lancashire  
United Kingdom  
BB11 5PW

Tel: 01706 815121  
sales@chapmangroup.co.uk  
www.chapmangroup.co.uk

Tel: 01706 815121  
sales@brisbanemoss.co.uk  
www.brisbanemoss.co.uk

Colour Fastness-								
		Grade	Change in Colour	Dark Colours				
				Cross Staining				
				Acetate	Cotton	Polyamide	Polyester	Acrylic Wool
Dry Cleaning	UNI EN ISO 105-D01		3	3	3	3	3	3
Dry Ironing	UNI EN ISO 105-X11		3	3	3	3	3	3
Wet Ironing	UNI EN ISO 105-X11		3	3	3	3	3	3
Acid Pers	UNI EN ISO 105-E04		3	3	2/3	3	3	3
Alkaline Pers	UNI EN ISO 105-E04		3	3	2/3	3	3	3
Water	UNI EN ISO 105-E01		3	3	2/3	3	3	3
Washing	UNI EN ISO 105-C06		3	3	2/3	3	3	3
Dry Rubbing	UNI EN ISO 105-X12				3/4			
Wet Rubbing	UNI EN ISO 105-X12				2			
Light	UNI EN ISO 105-B02	>4						

		Grade	Change in Colour	Light Colours				
				Cross Staining				
				Acetate	Cotton	Polyamide	Polyester	Acrylic Wool
Dry Cleaning	UNI EN ISO 105-D01		4	4	4	4	4	4
Dry Ironing	UNI EN ISO 105-X11		4	4	4	4	4	4
Wet Ironing	UNI EN ISO 105-X11		3	4	4	4	4	4
Acid Pers	UNI EN ISO 105-E04		4	4	4	4	4	4
Alkaline Pers	UNI EN ISO 105-E04		4	4	4	4	4	4
Water	UNI EN ISO 105-E01		4	4	4	4	4	4
Washing	UNI EN ISO 105-C06		4	4	4	4	4	4
Dry Rubbing	UNI EN ISO 105-X12				4			
Wet Rubbing	UNI EN ISO 105-X12				3			
Light	UNI EN ISO 105-B02	>4						

Chemical and Ecotoxicological-		
pH-value Water Extract	4.0 - 7.5	UNI EN ISO 3071
Flammability	Class 1	16 CFR 1610
Formaldehyde	< 16 mg/kg	UNI EN ISO 14184/1
Cancer-causing Aromatic Amines	< 20 ppm	DIN EN ISO 14362/1
REACH Compliant	Yes	Reg.(UE) 1907/2006
Standard(s)-		
Compliant with the National Standard of the People's Republic of China		GB18401-2010
Better Cotton Available		1030682-1

**BRISBANE  
MOSS**



<b>Test Report</b>	<b>No. 28515289</b>	<b>Date: 7<sup>th</sup> November 2024</b>	<b>Page 1 of 9</b>
--------------------	---------------------	---	--------------------

The following sample(s) was/were submitted and identified on behalf of the client as:

**Sample Description** : 8 Wale Heavyweight Corduroy  
**Customer** : **Brisbane Moss; Bridgeroyd Works, Todmorden, OL14 6DF**  
**Product type** : Apparel Fabric GS20 100% Cotton 565 gsm  
**PO Number** : 12227-1  
**Colour** : DK Olive/304  
**Contact person** : Stephen Newham, Joshua Barker-Lockwood

Test Performed : Selected test(s) as requested by applicant  
 \* \* \* \* \*  
 Sample Receiving Date : 17<sup>th</sup> October 2024  
 Testing Period : 17<sup>th</sup> October 2024 – 7<sup>th</sup> November 2024  
 Test Result(s) : For further details, please refer to the following page(s).

**Conclusion:**

Test Property			
Colour Fastness to Washing	Data	Tear Strength	Data
Colour Fastness to Dry Cleaning	Data	Seam Slippage	Data
Colour Fastness to Perspiration	Data	Pilling Resistance	Data
Colour Fastness to Water	Data	Abrasion Resistance	Data
Colour Fastness to Light*	Data	Yarn Count*	Data
Colour Fastness to Hot Pressing*	Data	Formaldehyde*	Pass
Colour Fastness to Rubbing	Data	pH Value	Data
Dimensional Stability to Washing	Data	Bow & Skew**	Data
Dimensional Stability to Dry Cleaning**	Data	Azo Dyes*	Pass
Dimensional Stability to Free Steam (wira)*	Data		
Tensile Strength	Data		

\*Sub Contracted tests withing TUV Group Laboratories (Turkey)

\*\*Not UKAS Accredited

Signed for and on behalf of  
TÜV Rheinland UK LTD

Christopher  
 Clarke  
 Digitally signed by  
 Christopher Clarke  
 Date: 2024.11.07  
 14:51:10 Z  
 Chris Clarke  
 Laboratory Supervisor



Test result is drawn according to the kind and extent of tests performed.

TÜV Rheinland (UK). Ltd, Unit 3, Key Point Office Village, Alfreton, DE55 7FQ,  
 United Kingdom Tel: +44 1773 300 362, Email: joanne.brown@uk.tuv.com, Internet: <http://www.tuv.com>





<b>Test Report</b>	<b>No. 28515289</b>	<b>Date: 7<sup>th</sup> November 2024</b>	<b>Page 2 of 9</b>
--------------------	---------------------	---	--------------------

Without permission of the test centre this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. This test report represents the test parameters as requested by the customer based on submitted samples only.

**Results:**

<b>Colour Fastness to Washing</b>	
Washing Condition: A2S, 30°C (Deviation) With ECE(B) + Sodium Perborate, 10 Steel Balls.	
<b>Sample</b>	<b>Result</b>
<b>Colour Change</b>	4-5
<b>Self-Staining</b>	-
<b>Colour Staining</b>	
<b>Acetate</b>	4-5
<b>Cotton</b>	3
<b>Polyamide</b>	4-5
<b>Polyester</b>	4-5
<b>Acrylic</b>	4-5
<b>Wool</b>	4-5
Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good	

<b>Colour Fastness to Water</b>	
BS EN ISO 105 E01: 2013	
<b>Sample</b>	<b>Result</b>
<b>Colour Change</b>	4-5
<b>Self-Staining</b>	-
<b>Colour Staining</b>	
<b>Acetate</b>	4-5
<b>Cotton</b>	2-3
<b>Polyamide</b>	4-5
<b>Polyester</b>	4-5
<b>Acrylic</b>	4-5
<b>Wool</b>	4-5
Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good	

<b>Colour Fastness to Rubbing</b>			
BS EN ISO 105 X12: 2016			
<b>Sample</b>	<b>Result</b>		
	<b>Warp</b>		<b>Weft</b>
	<b>Dry: 4-5</b>		<b>Dry: 4-5</b>
	<b>Wet: 3</b>	<b>% Soak: 100</b>	<b>Wet: 3</b> <b>% Soak: 100</b>
<b>Atmospheric Conditions: 65% RH, 20°C</b>			
<b>Conditioning time of sample and rubbing cloth: 4 Hours</b>			



<b>Test Report</b>	<b>No. 28515289</b>	<b>Date: 7<sup>th</sup> November 2024</b>	<b>Page 3 of 9</b>
--------------------	---------------------	---	--------------------

**Colour Fastness to Light**

BS EN ISO 105 B02 Method 3: 2013

Sample	
	>4

**Colour Fastness to Hot Pressing**

BS EN ISO 105 X11 @ 150°C: 1994

Sample	
Sample	Immediately After Testing Colour Change Dry: 4-5 Damp: 4-5 Wet: 4-5 After Conditioning Colour Change Dry: 4-5 Damp: 4-5 Wet: 4-5 Colour Staining Damp: 3 Wet: 1-2

**Colour Fastness to Dry Cleaning**

BS EN ISO 105-D01: 2010

	Result
Colour Change	4-5
Self-Staining	-
Colour Staining	Result
Acetate	4-5
Cotton	4-5
Polyamide	4-5
Polyester	4-5
Acrylic	4-5
Wool	4-5

Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good



<b>Test Report</b>	No. 28515289	Date: 7 <sup>th</sup> November 2024	Page 4 of 9
--------------------	--------------	-------------------------------------	-------------

Colour Fastness To Perspiration BS EN ISO 105-E04: 2013		
Sample	Result	
	Acid	Alkaline
Colour Change	4-5	4-5
Self-Staining	-	-
Colour Staining	Result	Result
Acetate	4-5	4-5
Cotton	3	3
Polyamide	4-5	4-5
Polyester	4-5	4-5
Acrylic	4-5	4-5
Wool	4-5	4-5
Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good		

Abrasion Resistance (BS EN ISO 12947-2:2016/AC:2006); Martindale Wear & Abrasion Tester; 9 kPa Pressure) The criterion for judging end point was Two Threads Broken			
Result			
	Specimen 1	Specimen 2	Specimen 3
No Two Thread Breakdown	30,000	30,000	30,000
Colour Change At 3000 (rubs)	4-5	4-5	4-5
Remarks: Grey Scale Rating is based on the step scale of 1 to 5, where 1 is bad and 5 is good Observation Technique:40 fold magnification			

Pilling Resistance (BS EN ISO 12945-2:2020; Martindale Abrasion & Pilling Tester; Tested against self No cleansing required	
	Average Result
After 2000 Rubs Rating	P: 4-5 F: 4-5 M: 4-5
P=Pilling F=Fuzzing M=Matting	

<b>Test Report</b>	<b>No. 28515289</b>	<b>Date: 7<sup>th</sup> November 2024</b>	<b>Page 5 of 9</b>
--------------------	---------------------	---	--------------------

<b>Tensile Strength</b> (BS EN ISO 13934-1:2013)	
<b>Direction</b>	<b>Result</b>
Warp	183.4 kg
Weft	120.5 kg

<b>Dimensional Change After Washing</b> BS EN ISO 6330: 2012 3N @ 30°C Flat Dry	
<b>Direction</b>	<b>%Change</b>
Warp	0.0 %
Weft	-0.2 %

<b>Dimensional Change After Commercial Dry Cleaning</b> (Commercial dry clean cycle)	
<b>Direction</b>	<b>%Change</b>
Warp	-2.9 %
Weft	-0.3 %

<b>Dimensional Change to Free Steam (wira)</b> BS 4323: 1979	
<b>Direction</b>	<b>%Change</b>
Warp	-0.5
Weft	-0.5





<b>Test Report</b>	No. 28515289	Date: 7 <sup>th</sup> November 2024	Page 6 of 9
--------------------	--------------	-------------------------------------	-------------

<b>Bow &amp; Skewness</b> ISO 13015: 2013	
<b>Direction</b>	
Bow	0.0 %
Skew	0.0 %

<b>Yarn Count</b> ISO 7211-5 Method A	
<b>Sample</b>	<b>Result</b>
	Warp: Nm: 11.7, Ne: 6.9 Weft: Nm: 26.2, Ne: 15.4  Nm: Metric Count Ne: Cotton Count

<b>Formaldehyde Content</b> ISO 14184-1: 2011	
<b>Sample</b>	<b>Result</b>
	Not Detected <16 mg/kg

<b>pH Value</b> ISO 3071: 2005 (withdrawn)	
<b>Sample</b>	<b>Result</b>
	pH 7.34
pH value of Grade 3 water: 7.1	
Temperature of the Grade 3 water: 20.3	



**TÜVRheinland®**

Precisely Right.

Softlines

<b>Test Report</b>	<b>No. 28515289</b>	<b>Date: 7<sup>th</sup> November 2024</b>	<b>Page 7 of 9</b>
--------------------	---------------------	---	--------------------

<b>Seam Slippage</b> BS EN ISO 13936-1: 2004 6mm SO	
Sample	Result
Warp	>20.4 kg
Weft	>20.4 kg
Remarks:	

<b>Tearing Strength</b> BS EN ISO 13937-2: 2000	
Sample	Result
Warp	2931.9 g
Weft	2219.9 g

<b>Test Report</b>	<b>No. 28515289</b>	<b>Date: 7<sup>th</sup> November 2024</b>	<b>Page 8 of 9</b>
--------------------	---------------------	---	--------------------

#### 4. Banned azo dyes

Test Method: Method 1 - EN ISO 14362-1:2017 (Textiles) (Buffer extraction)  
Method 2 - EN ISO 14362-1:2017 (Textiles) (Xylene extraction)  
Method 3 - ISO 17234-1:2020 (Leather)  
Method 4 - EN ISO 14362-3:2017 (Textile, 4-aminoazobenzene confirmation)  
Method 5 - ISO 17234-2:2011 (Leather, 4-aminoazobenzene confirmation)

#### Test Results:

		Material No. M001				
		Test No. T001-1				
		Method No. Method 1				
		A22 Confirmation Method No. --				
ID	Test Parameter	CAS NO	Unit	RL	Regulatory Requirement	Result
A1	4-Aminobiphenyl	92-67-1	mg/kg	5	30	n.d.
A2	Benzidine	92-87-5	mg/kg	5	30	n.d.
A3	4-Chloro-o-toluidine	95-69-2	mg/kg	5	30	n.d.
A4	2-Naphthylamine	91-59-8	mg/kg	5	30	n.d.
A5*	o-Aminoazotoluene	97-56-3	mg/kg	5	30	n.d.
A6*	5-nitro-o-toluidine / 2-Amino-4-nitrotoluene	99-55-8	mg/kg	5	30	n.d.
A7	4-Chloroaniline	106-47-8	mg/kg	5	30	n.d.
A8	4-methoxy-m-phenylenediamine / 2,4-Diaminoanisole	615-05-4	mg/kg	5	30	n.d.
A9	4,4'-Diaminodiphenylmethane	101-77-9	mg/kg	5	30	n.d.
A10	3,3'-Dichlorobenzidine	91-94-1	mg/kg	5	30	n.d.
A11	3,3'-Dimethoxybenzidine	119-90-4	mg/kg	5	30	n.d.
A12	3,3'-Dimethylbenzidine	119-93-7	mg/kg	5	30	n.d.
A13	4,4'-methylenedi-o-toluidine / 3,3'-Dimethyl-4,4'-diaminodiphenylmethane	838-88-0	mg/kg	5	30	n.d.
A14	p-Cresidine	120-71-8	mg/kg	5	30	n.d.
A15	4,4'-Methylene-bis-(2-chloroaniline)	101-14-4	mg/kg	5	30	n.d.
A16	4,4'-Oxydianiline	101-80-4	mg/kg	5	30	n.d.
A17	4,4'-Thiodianiline	139-65-1	mg/kg	5	30	n.d.
A18	o-Toluidine	95-53-4	mg/kg	5	30	n.d.
A19	4-methyl-m-phenylenediamine / 2,4-Toluyldiamine	95-80-7	mg/kg	5	30	n.d.
A20	2,4,5-Trimethylaniline	137-17-7	mg/kg	5	30	n.d.
A21	O-Anisidine	90-04-0	mg/kg	5	30	n.d.
A22**	4-Aminoazobenzene	60-09-3	mg/kg	5	30	n.d.
A23^	2,4-xylidine	95-68-1	mg/kg	5	30	n.d.
A24^	2,6-xylidine	87-62-7	mg/kg	5	30	n.d.
*2	2-Naphthyl-ammoniumacetate	553-00-4	mg/kg	5	30	n.d.
A26	4-chloro-o-toluidinium chloride	3165-93-3	mg/kg	5	30	n.d.
A25	4-chloro-o-toluidinium chloride	3165-93-3	mg/kg	5	30	n.d.
A27	4-Methoxy-m-phenylene diammonium sulphate	39156-41-7	mg/kg	5	30	n.d.
A28	2,4,5-trimethylaniline hydrochloride	21436-97-5	mg/kg	5	30	n.d.



<b>Test Report</b>	<b>No. 28515289</b>	<b>Date: 7<sup>th</sup> November 2024</b>	<b>Page 9 of 9</b>
--------------------	---------------------	---	--------------------

**Remark:**

- \* The CAS-number 97-56-3 (A5) and 99-55-8 (A6) are further reduced to CAS-number 95-53-4 (A18) and 95-80-7 (A19).
- \*\* Azo colorants that are able to form 4-aminoazobenzene (A22) CAS-number 60-09-3, generate under the condition of this method Aniline (CAS-number 62-53-3) and 1,4-phenylenediamine (CAS-number 106-50-3.)
- \*\*\* Azo colorants that are able to form 4-aminoazobenzene (A22), is confirmed by EN ISO 14362-3:2017 / ISO 17234-2:2011.
- \*\*\*\* Azo colorants are detected & quantified by GC/MS and confirmed by HPLC/DAD or HPLC/MSMS.

-End of Test Report-

<b>Test Report</b>	<b>No. 28515281</b>	<b>Date: 6<sup>th</sup> November 2024</b>	<b>Page 1 of 4</b>
--------------------	---------------------	---	--------------------

The following sample(s) was/were submitted and identified on behalf of the client as:

**Sample Description** : 8 Wale Heavyweight Corduroy  
**Customer** : **Brisbane Moss; Bridgeroyd Works, Todmorden, OL14 6DF**  
**Product type** : Apparel GS20 100% Cotton 565 gsm  
**PO Number** : 11110-10A  
**Colour** : Corn/980  
**Contact person** : Stephen Newham, Joshua Barker-Lockwood

Test Performed : Selected test(s) as requested by applicant  
\* \* \* \* \*  
Sample Receiving Date : 17<sup>th</sup> October 2024  
Testing Period : 17<sup>th</sup> October 2024 –  
Test Result(s) : For further details, please refer to the following page(s).

**Conclusion:**

Test Property	
Colour Fastness to Washing	Data
Colour Fastness to Dry Cleaning	Data
Colour Fastness to Perspiration	Data
Colour Fastness to Water	Data
Colour Fastness to Light*	Data
Colour Fastness to Hot Pressing*	Data
Colour Fastness to Rubbing	Data

\*Sub Contracted tests withing TUV Group Laboratories (Turkey)

\*\*Not UKAS Accredited

Signed for and on behalf of  
TÜV Rheinland UK LTD

Christopher Clarke  
Digitally signed by  
Christopher Clarke  
Date: 2024.11.06 15:01:39 Z

**Chris Clarke**  
**Laboratory Supervisor**



8400

*Test result is drawn according to the kind and extent of tests performed.  
Without permission of the test centre this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. This test report represents the test parameters as requested by the customer based on submitted samples only.*

<b>Test Report</b>	No. 28515281	Date: 6 <sup>th</sup> November 2024	Page 2 of 4
--------------------	--------------	-------------------------------------	-------------

**Results:**

<b>Colour Fastness to Washing</b> Washing Condition: A2S, 30°C (Deviation) With ECE(B) + Sodium Perborate, 10 Steel Balls.	
Sample	Result
Colour Change	4-5
Self-Staining	-
Colour Staining	
Acetate	4-5
Cotton	4
Polyamide	4-5
Polyester	4-5
Acrylic	4-5
Wool	4-5
Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good	

<b>Colour Fastness to Water</b> BS EN ISO 105 E01: 2013	
Sample	Result
Colour Change	4-5
Self-Staining	-
Colour Staining	
Acetate	4-5
Cotton	4
Polyamide	4-5
Polyester	4-5
Acrylic	4-5
Wool	4-5
Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good	

Colour Fastness to Rubbing				
BS EN ISO 105 X12: 2016				
Sample	Result			
	Warp		Weft	
	Dry: 4-5	Wet: 4	Dry: 4-5	Wet: 4
Atmospheric Conditions: 65% RH, 20°C				
Conditioning time of sample and rubbing cloth: 4 Hours				



<b>Test Report</b>	No. 28515281	Date: 6 <sup>th</sup> November 2024	Page 3 of 4
--------------------	--------------	-------------------------------------	-------------

<b>Colour Fastness to Light</b> BS EN ISO 105 B02 Method 3: 2013	
<b>Sample</b>	
	>4

<b>Colour Fastness to Hot Pressing</b> BS EN ISO 105 X11 @ 150°C: 1994	
<b>Sample</b>	
Sample	<p>Immediately After Testing Colour Change</p> <p>Dry: 4-5 Damp: 4-5 Wet: 4-5</p> <p>After Conditioning Colour Change</p> <p>Dry: 4-5 Damp: 4-5 Wet: 4-5</p> <p>Colour Change</p> <p>Damp: 4-5 Wet: 3</p>

<b>Colour Fastness to Dry Cleaning</b> BS EN ISO 105-D01: 2010	
	<b>Result</b>
<b>Colour Change</b>	4-5
<b>Self-Staining</b>	-
<b>Colour Staining</b>	
Acetate	4-5
Cotton	4-5
Polyamide	4-5
Polyester	4-5
Acrylic	4
Wool	4-5
Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good	

<b>Test Report</b>	No. 28515281	Date: 6 <sup>th</sup> November 2024	Page 4 of 4
--------------------	--------------	-------------------------------------	-------------

Colour Fastness To Perspiration BS EN ISO 105-E04: 2013		
Sample	Result	
	Acid	Alkaline
Colour Change	4-5	4-5
Self-Staining	-	-
Colour Staining	Result	Result
Acetate	4-5	4-5
Cotton	4	4
Polyamide	4-5	4-5
Polyester	4-5	4-5
Acrylic	4-5	4-5
Wool	4-5	4-5
Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good		

-End of Test Report-

<b>Test Report</b>	<b>No. 28515607</b>	<b>Date: 14<sup>th</sup> February 2025</b>	<b>Page 1 of 8</b>
--------------------	---------------------	--	--------------------

The following sample(s) was/were submitted and identified on behalf of the client as:

**Sample Description** : 8 Wale Heavyweight Corduroy  
**Customer** : **Brisbane Moss; Bridgeroyd Works, Todmorden, OL14 6DF**  
**Product type** : Apparel GS20 100% Cotton 565 g/m<sup>2</sup>  
**PO Number** : 13598-0C  
**Colour** : Black / 3213  
**Contact person** : Stephen Newham, Joshua Barker-Lockwood

Test Performed : Selected test(s) as requested by applicant  
 Sample Receiving Date : 3<sup>rd</sup> February 2025  
 Testing Period : 3<sup>rd</sup> February 2025 – 14<sup>th</sup> February 2025  
 Test Result(s) : For further details, please refer to the following page(s).

**Conclusion:**

Test Property – REACH Annex XVII	
Aromatic Amine Salts*	Pass
Dimethyl Fumarate*	Pass
Migration of Heavy Metals*	Pass
Flame Retardants*	Pass
AP + APEO (Alkylphenols, Alkylphenol Ethoxylates)*	Pass
Quinoline*	Pass
Polycyclic Aromatic Hydrocarbons (PAHs)*	Pass
Pentachlorophenol (PCP) Content*	Pass
Per – and Polyfluoroalkyl Substances (PFAS)*	Pass
Organotin Compounds Content*	Pass

\*Sub Contracted tests withing TUV Group Laboratories (Turkey)

\*\*Not UKAS Accredited

Signed for and on behalf of  
TÜV Rheinland UK LTD

**Christopher  
Clarke**

Digitally signed by  
Christopher Clarke  
Date: 2025.02.14 12:03:03 Z

**Chris Clarke**  
**Laboratory Supervisor**

Test result is drawn according to the kind and extent of tests performed.  
Without permission of the test centre this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. This test report represents the test parameters as requested by the customer based on submitted samples only.



<b>Test Report</b>	<b>No. 28515607</b>	<b>Date: 14<sup>th</sup> February 2025</b>	<b>Page 2 of 8</b>
--------------------	---------------------	--	--------------------

Material No.	Material	Color	Location
M001	Textile	Black	Velour woven base

### Results:

#### 1. Aromatic Amine Salts

**Test Method:** DIN EN ISO 14362-1:2017  
DIN EN ISO 14362-3:2017  
Analyzed by GC-MSD

#### Test Result:

Test No. T001					Material No. M001
Test Parameter	CAS NO	Unit	RL	Regulatory Requirement	Result
4-chloro-o-toluidinium chloride	3165-93-3	mg/kg	5	30	n.d.
4-methoxy-m-phenylene diammonium sulphate; 2,4-diaminoanisole sulphate	39156-41-7	mg/kg	5	30	n.d.
2,4,5-trimethylaniline hydrochloride	21436-97-5	mg/kg	5	30	n.d.
2-Naphthyl-ammoniumacetate	553-00-4	mg/kg	5	30	n.d.
Conclusion	-				

**Abbreviation:** n.d. = Not Detected (< Reporting Limit)  
RL = Reporting Limit  
mg/kg = milligram per kilogram

#### 2. Dimethyl fumarate (CAS No. 624-49-7)

**Test Method:** Organic solvent extraction, GCMS analysis

#### Test Result:

Test No.	Material No.	Test Parameter	Unit	RL	Regulatory Requirement	Test Result
T001	M001	Dimethyl fumarate	mg/kg	0.025	0.1	n.d.

**Abbreviation:** < = less than  
RL = Reporting Limit  
mg/kg = milligram per kilogram

**Test Report**

No. 28515607

Date: 14<sup>th</sup> February 2025

Page 3 of 8

**3. Migration of Heavy Metals**

Test Method: All materials except leather: DIN EN 16711-2:2016  
Leather: DIN EN ISO 17072-1:2019

**Test Result:**

Test No.				T001
Material No.				M001
Test Parameter	Unit	RL	Customer Requirement	Result
Arsenic (As)	mg/kg	0.1	< 1 mg/kg each	n.d.
Cadmium (Cd)	mg/kg	0.05	< 1 mg/kg each	n.d.
Chromium (Cr)	mg/kg	0.5	< 1 mg/kg each	n.d.
Lead (Pb)	mg/kg	0.2	< 1 mg/kg each	n.d.
Conclusion				Pass

**Abbreviation:** < = less than  
RL = Reporting Limit  
mg/kg = milligram per kilogram

**TÜVRheinland®**

Precisely Right.

Softlines

Test Report	No. 28515607	Date: 14 <sup>th</sup> February 2025	Page 4 of 8
-------------	--------------	--------------------------------------	-------------

**4. Flame Retardants**

Test Method: 1. Organic solvent extraction, GCMS/LCMSMS  
2. Acid digestion, analyzed by ICP-MS

Test No. T001					T001
Material No. M001					M001
Test Parameter	CAS No.	Unit	RL	Formulation Limit	Test Result
Octabromodiphenyl ether (OctaBDE)	32536-52-0	mg/kg	100	< 1000 mg/kg	n.d.
Tris(2-chloroethyl)phosphate (TCEP)	115-96-8	mg/kg	100	< 1000 mg/kg	n.d.
Tris(2,3-dibromopropyl)phosphate (TRIS)	126-72-7	mg/kg	100	not used	n.d.
Decabromodiphenyl ether (DecaBDE)	1163-19-5	mg/kg	100	< 1000 mg/kg	n.d.
Pentabromodiphenyl ether (PentaBDE)	32534-81-9	mg/kg	100	< 500 mg/kg	n.d.
Tris(1-aziridinyl)phosphineoxide (TEPA)	545-55-1	mg/kg	100	not used	n.d.
Polybromobiphenyls (PBB)	59536-65-1	mg/kg	100	not used	n.d.
Hexabromocyclododecane (HBCDD)	3194-55-6	mg/kg	100	< 100 mg/kg	n.d.
Heptabromodiphenyl ether (HeptaBDE)	68928-80-3	mg/kg	100	< 500 mg/kg	n.d.
Hexabromodiphenyl ether (HexaBDE)	36483-60-0	mg/kg	100	< 500 mg/kg	n.d.
Tetrabromodiphenyl ether (TetraBDE)	40088-47-9	mg/kg	100	< 500 mg/kg	n.d.

**Abbreviation:** < = less than  
RL = Reporting Limit  
ppm = part per million



**TÜVRheinland®**

Precisely Right.

Softlines

Test Report	No. 28515607	Date: 14 <sup>th</sup> February 2025	Page 5 of 8
-------------	--------------	--------------------------------------	-------------

**5.AP + APEO (Alkylphenols, Alkylphenol Ethoxylates)**

Test Method: ISO 18254-1:2016  
NP and OP: Organic solvent extraction, GCMS  
NPEO and OPEO: Organic solvent extraction, LC-MS

**Test Result:**

Test No.	Material No.	Test Parameter	Unit	RL	Regulatory Requirement	Test Result
T001	M001	Nonylphenols (NP)	mg/kg	5	-	n.d.
		Octylphenols (OP)	mg/kg	5	-	n.d.
		Nonylphenoethoxylates (NPEO)	mg/kg	20	< 100 mg/kg	n.d.
		Octylphenoethoxylates (OPEO)	mg/kg	20	< 100 mg/kg	n.d.

**Abbreviation:** n.d. = not detected (< Reporting Limit)  
RL = Reporting Limit  
mg/kg = milligram per kilogram  
NA = Not Applicable

**6.Quinoline**

Test Method: Ref. to DIN 54231:2022

**Test Result:**

Test No.	Material No.	Test Parameter	CAS No.	Unit	RL	Regulatory Requirement	Test Result	Conclusion
T001	M001	Quinoline	91-22-5	mg/kg	10	50	n.d.	Pass

**Abbreviation:** < = less than  
RL = Reporting Limit  
mg/kg = milligram per kilograms



<b>Test Report</b>	<b>No. 28515607</b>	<b>Date: 14<sup>th</sup> February 2025</b>	<b>Page 6 of 8</b>
--------------------	---------------------	--	--------------------

## 7. Polycyclic aromatic hydrocarbons (PAHs)

Test Method: AfPS GS 2019:01

### Test Result:

Test No. T001					T001
Material No. M001					M001
Test Parameter	CAS NO	Unit	RL	Regulatory Requirement	Result
Benzo[a]anthracene	56-55-3	mg/kg	0.2	< 1 mg/kg	n.d.
Benzo[a]pyrene (BaP)	50-32-8	mg/kg	0.2	< 1 mg/kg	n.d.
Benzo[b]fluoranthene	205-99-2	mg/kg	0.2	< 1 mg/kg	n.d.
Benzo[k]fluoranthene	207-08-9	mg/kg	0.2	< 1 mg/kg	n.d.
Benzo[j]fluoranthene	205-82-3	mg/kg	0.2	< 1 mg/kg	n.d.
Benzo[e]pyrene	192-97-2	mg/kg	0.2	< 1 mg/kg	n.d.
Chrysene	218-01-9	mg/kg	0.2	< 1 mg/kg	n.d.
Dibenzo[a,h]anthracene	53-70-3	mg/kg	0.2	< 1 mg/kg	n.d.
Naphthalene	91-20-3	mg/kg	0.2	< 1 mg/kg	n.d.
Anthracene	120-12-7	mg/kg	0.2	Sum 10	n.d.
Benzo[g,h,i]perylene	191-24-2	mg/kg	0.2		n.d.
Fluoranthene	206-44-0	mg/kg	0.2		n.d.
Indeno[1,2,3-cd]pyrene	193-39-5	mg/kg	0.2		n.d.
Phenanthrene	85-01-8	mg/kg	0.2		n.d.
Pyrene	129-00-0	mg/kg	0.2		n.d.

**Abbreviation:** < = less than  
RL = Reporting Limit  
NA = Not Applicable  
mg/kg = milligram per kilogram

## 8. Pentachlorophenol (PCP) Content

Test Method: Ref. to 64 LFGB B82.02-8:2001

### Test result

Test No.	Material No.	Test Parameter	Unit	RL	Regulatory Requirement	Test Result
T001	M001	Pentachlorophenol (PCP)	mg/kg	0.1	≤ 5 mg/kg	n.d.

**Abbreviation:** < = less than  
RL = Reporting Limit  
mg/kg = milligram per kilogram

<b>Test Report</b>	<b>No. 28515607</b>	<b>Date: 14<sup>th</sup> February 2025</b>	<b>Page 7 of 8</b>
--------------------	---------------------	--	--------------------

#### 9.Per-and polyfluoroalkyl substances(PFAS)

Test Method: Reference EN 17681-1:2022/EN 17681-2:2022, determination by CI-GCMS, GC-MSMS and LC-MSMS.

#### Test Result:

Test No.					T001
Material No.					M001
Test Parameter	CAS NO	Unit	RL	Customer's requirement	Result
Perfluorooctanesulfonic acid (PFOS)	1763-23-1	µg/m <sup>2</sup>	1	< 1 µg/m <sup>2</sup>	n.d.
Perfluorooctane sulfonamide (PFOSA)	754-91-6	µg/m <sup>2</sup>	1	< 1 µg/m <sup>2</sup>	n.d.
Perfluorooctanoic acid (PFOA)	335-67-1	µg/m <sup>2</sup>	1	< 1 µg/m <sup>2</sup>	n.d.
Sodium perfluorooctanoate (PFOA-Na)	335-95-5	mg/kg	1	< 1 µg/m <sup>2</sup>	n.d.
Potassium perfluorooctanoate (PFOA-K)	2395-00-8	mg/kg	1	< 1 µg/m <sup>2</sup>	n.d.
Silver perfluorooctanoate (PFOA-Ag)	335-93-3	mg/kg	1	< 1 µg/m <sup>2</sup>	n.d.
Perfluorooctanoyl fluoride (PFOA-F)	335-66-0	mg/kg	1	< 1 µg/m <sup>2</sup>	n.d.
Ammonium pentadecafluorooctanoate (APFO)	3825-26-1	mg/kg	1	< 1 µg/m <sup>2</sup>	n.d.
Perfluorohexane sulfonic acid (PFHxS)	355-46-4	mg/kg	1	< 1 µg/m <sup>2</sup>	n.d.
1H,1H,2H,2H-Perfluorododecanol (10:2 FTOH)	865-86-1	mg/kg	1	< 1 µg/m <sup>2</sup>	n.d.
Perfluorocycloethanol 8:2 (8:2 FTOH)	678-39-7	mg/kg	1	< 1 µg/m <sup>2</sup>	n.d.
Conclusion					Pass

**Abbreviation:** < = Less than  
 RL = Reporting Limit  
 mg/kg = milligram per kilogram  
 µg/m<sup>2</sup> = microgram per square metre

**Test Report**

No. 28515607

Date: 14<sup>th</sup> February 2025

Page 8 of 8

**10.Organotin compounds content**

Test Method: Organic solvent extraction, GCMS  
Ref. to ISO/TS 16179:2012

Test No.				T001
Material No.				M001
Test Parameter	Unit	RL	Regulatory Requirement	Result
TBT(Tributyltin) by weight of tin	%	0.01	< 0.1 %	n.d.
TPT(Triphenyltin) by weight of tin	%	0.01	< 0.1 %	n.d.
TOT(Trioctyltin) by weight of tin	%	0.01	< 0.1 %	n.d.
TCyT(Tricyclohexyltin) by weight of tin	%	0.01	< 0.1 %	n.d.
TPrT(Tripnpyltn) by weight of tin	%	0.01	< 0.1 %	n.d.
Sum of Tin of tri-substituted organotins	%	NA	< 0.1 %	n.d.
DBT(Dibutyltin) by weight of tin	%	0.01	< 0.1 %	n.d.
DOT(Dioctyltin) by weight of tin	%	0.01	< 0.1 %	n.d.

**Abbreviation:** < = less than  
RL = Reporting Limit  
% = percentage  
NA = Not Applicable

-End of Test Report-



**BV CPS TEST LABORATUVARLARI LTD. STI.  
BUREAU VERITAS CONSUMER PRODUCTS  
SERVICES**

Yalcin Kores Cad. No:22 Erdinc Binalari  
A Blok 1.Kule 1.Kat 34209 Gunesli, Istanbul / Turkey  
Tel:+90.212.494 35 35 Fax:+90.212.494 35 60  
email:info.turkey@bvcp.com.tr  
website: www.bureauveritas.com/cps



Test TS EN ISO/IEC 17025 AB-0505-T
AB-0505-T
72252870332
10-25

## TEST REPORT

**LAB LOCATION: TURKEY**

**SERVICE TYPE: Regular**

**LAB NUMBER: (7225)287-0332**

**THE DATE OF RECEIPT OF TEST ITEM: October 14, 2025**

**START DATE FOR TESTING: October 14, 2025**

**DATE END OF TEST: October 16, 2025**

**NUMBER OF WORKING DAYS: 3.0**

**CUSTOMER NAME / ADDRESS CONTACT NAME** : M CHAPMAN&SONS LTD  
(Address: Chapman Works, Manchester Road,Dunnockshaw,Bumley  
BB121 5PW)  
(Attn: Paige Newham-Foulds)

**BUYER** : /

**SUPPLIER REFERENCE** : Style Number: /  
PO Number: 13207  
Unique Product Code: 3213

**SAMPLE DESCRIPTION** : GS20  
(Claimed Fiber Content: 100% Cotton)  
(Claimed Fabric Weight: /)

**COLOUR** : Black

**SUBMITTED CARE INSTRUCTION:** :

**REASON FOR REVISION** : /



**Date Out**  
(16/10/2025)

**Ali Payalan**  
Senior Client Team Lead

**Hasan Altıngül**  
Deputy General Manager Operations  
(16/10/2025)

BV CPS Test Laboratuvarları Ltd. Sti. accredited by TÜRKAK under registration number AB-0505-T for TS EN ISO/IEC 17025:2017 as test laboratory. Turkish Accreditation Agency (TÜRKAK) is a signatory to the European co-operation for Accreditation (EA) Multilateral Agreement (MLA) and to the International Laboratory Accreditation Cooperation (ILAC) Mutual Recognition Arrangement (MRA) for the recognition of test reports. This report is governed by, and incorporates by reference, the Conditions of Testing as posted at the date of issuance of this report at <http://www.bureauveritas.com/home/about-us/our-business/cps/about-us/terms-conditions/> and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. Measurement uncertainty is only provided upon request for accredited tests. The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report. Statements of conformity are based on simple acceptance criteria without taking measurement uncertainty into account, unless otherwise requested in writing. You have 60 days from the date of issuance of this report to notify us of any material error or omission caused by our negligence or if you require measurement uncertainty, provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents. Testing reports without signature are not valid. BV CPS Test Laboratories is not responsible for deviations for the accuracy of the information provided by the customer that may affect the validity of the test results. Test results given in this test report represent only the sample(s) delivered to the laboratory, as sent to BV CPS Test Laboratories by the client/vendor via courier, cargo and/or manual delivery. No sampling is performed by BV CPS Test Laboratories.




**SUMMARY OF TEST RESULTS**

TEST PERFORMED	PASS	FAIL	DATA
Flammability Of Clothing Textiles*	X		
<b>* TURKAK Accredited- See Appendix A</b>			

REMARKS		
1	:	P: Pass, F: Fail, DATA: No Evaluation, N/A: Not Applicable
2	:	*The reported expanded uncertainty is based on the standard uncertainty multiplied by a coverage factor of k=2, providing a level of confidence of approximately 95%. Unless otherwise is specified, the uncertainty of measurement has not been taken into account when assessing pass/fail of the sample against the requirements of the standard. In case consideration of measurement uncertainties when assessing pass/ fail limits, some results may be in borderline. Information on uncertainty is contained in appendix A on this report.
3	:	The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.

**ORIGINAL**  
(SAMPLE IMAGE)



**TEST RESULTS**
**REQUIREMENTS**
**FLAMMABILITY OF CLOTHING TEXTILES (16 CFR 1610)**
**SAMPLE DESCRIPTION:** GS20

**FIBER CONTENT:** 100% COTTON

**FABRIC WEIGHT:** /

**FABRIC SURFACE:** RAISED FIBER SURFACE

**DIRECTION TO BE TESTED:** FACE / LENGTHWISE  
(FROM PRELIMINARY TEST)

**AS RECEIVED**
**AFTER REFURBISHING**

TIME OF FLAME  
SPREAD (S)

BURN CODE

TIME OF FLAME  
SPREAD (S)

BURN CODE

1	/	1	SF POI	P1	/	P1	SF POI
2	/	2	SF POI	P2	/	P2	SF POI
3	/	3	SF POI	P3	/	P3	SF POI
4	/	4	SF POI	P4	/	P4	SF POI
5	/	5	SF POI	P5	/	P5	SF POI

AVG. \_\_\_/\_\_\_ SECONDS FOR# \_\_\_/\_\_\_ SPECIMENS

AVG. \_\_\_/\_\_\_ SECONDS FOR# \_\_\_/\_\_\_ SPECIMENS

DNI DID NOT IGNITE.

IBE IGNITED, BUT EXTINGUISHED.

SF UC SURFACE FLASH, UNDER THE STOP THREAD, BUT DOES NOT BREAK THE STOP THREAD.

SF PW SURFACE FLASH, PART WAY. NO TIME SHOWN BECAUSE THE SURFACE FLASH DID NOT REACH THE STOP THREAD.

SF POI SURFACE FLASH, AT THE POINT OF IMPINGEMENT ONLY. (EQUIVALENT TO "DID NOT IGNITE" FOR PLAIN SURFACES.)

0.0 SEC. ACTUAL BURN TIME MEASURED AND RECORDED BY THE TIMING DEVICE.

0.0 SF ONLY TIME IN SECONDS, SURFACE FLASH ONLY. NO DAMAGE TO THE BASE FABRIC.

0.0 SFBB TIME IN SECONDS, SURFACE FLASH BASE BURN STARTING AT PLACES OTHER THAN THE POINT OF IMPINGEMENT AS A RESULT OF SURFACE FLASH.

0.0 SFBB POI TIME IN SECONDS, SURFACE FLASH BASE BURN STARTING AT THE POINT OF IMPINGEMENT. THIS RESULT DOES NOT QUALIFY AS A BASE BURN UNDER THE CURRENT INTERPRETATION OF PART OF 16 CFR PART 1610.

0.0 SFBB POI\* TIME IN SECONDS, SURFACE FLASH BASE BURN POSSIBLY STARTING AT THE POINT OF IMPINGEMENT. THE ASTERISK (\*) IS ACCOMPANIED BY THE FOLLOWING STATEMENT: "UNABLE TO MAKE ABSOLUTE DETERMINATION AS TO SOURCE OF BASE BURNS." THIS STATEMENT IS ADDED TO THE RESULT OF ANY SPECIMEN IF THERE IS A QUESTION AS TO ORIGIN OF THE BASE BURN.

**COMMENTS:** PASS CLASS 1, NORMAL FLAMMABILITY OF COMMERCIAL STANDARD 16 CFR 1610, FORMERLY 191-53 OF UNITED STATES FLAMMABILITY FABRIC ACT.

\*\*INDICATES DOES NOT MEET THE REQUIREMENTS

**APPENDIX A -LIST OF MEASUREMENT UNCERTAINTIES**

TEST NAME	STANDARD NAME	MEASUREMENT UNCERTAINTY
FLAMMABILITY OF CLOTHING TEXTILES	16 CFR 1610	±7,9 %

**-END OF REPORT-**